

Technical Bulletin 133

Test Results for August Chairs / Seating Units Recorded by U.S. Testing Company						
Series	Fabric	Heat Rise @ 4 Ft.	Heat Rise @ Ceiling	Weight Loss	Carbon Monoxide	Smoke Opacity
Maximum Allowed:		50° F.	200° F.	3.00 lbs.	1000 ppm	75%
Laurel Series						
3301	Karma	14.4 °	53.9 °	0.10 lb.	14 ppm	3%
3301	Tuffalo	72.3	74.4	0.2	2.3	9
3301	Tarpon W.	13.8	44.8	0.1	107	3
3301	Marquee	7.9	51.5	0	10	7
3301	Monet	7.4	52.6	0.5	33	12
3301	Deva	9.8	50.2	0	101	3
3301	Jaipur	10	62	0.25	19	2
3301	SugarSpice	5.5	62.8	0.5	220	22
3301	WindSong	12.5	74.1	0.5	14	4
3301	Moorea	4.7	41.3	0.1	29	13
3301	Radiance	10	85.8	0	5	2
3301	""Spirit II""	23.1	67.3	0	32	4
3301	Tuffalo	72.3	74.4	0.2	2.3	2
3301	Polyolefin	70	37	0	239	2
3301	TreviraFR	10.7	69.7	0	27	2
Linn Series						
3001	Karma	12.4°	46.3°	0.50 lb.	220 ppm	43%
3001	Moorea	5	47.9	0	90	3
3001	Tiara	8.3	43.3	0.5	22	15
3001	Deva	19.1	33.8	0.3	10	26
3001	TreviraFR	8.1	33.8	0.3	24	6
Lacara Series						
5031	Radiance	5.2°	49.2 °	0.50 lb	135 ppm	7%
5031	Opal	12.6	48.8	0.5	220	50
5005	TreviraFR	4.3	69.3	0	11	17
August						
803	Tiara	7.9°	50.6°	0.00 lb.	25ppm	5%
803	Tucson	3.4	56	0	49	6
LS Series						
7301	Worsted Wool	66.4°	13.3°	0.0 lb.	26 ppm	28.5%
7301	Tuffalo	89	17	0	35	1
LS Jr. & Laurel Jr. Series						
3401 / 401	Tuffalo	77	25	0	30	16%